

ABSTRACT

An asphalt composition comprising 0.5 to 50 parts by weight of a block copolymer component (I), 100 parts by weight of an asphalt (II) and 0.01 to 10 parts by weight of at least one vulcanizing agent (III) selected from the group consisting of sulfur and a sulfur-containing compound, wherein the block copolymer component (I) comprises at least one modified block copolymer comprising an unhydrogenated or hydrogenated base block copolymer comprising at least one vinyl aromatic polymer block (A) and at least one conjugated diene polymer block (B), and a functional group-containing modifier group bonded to the base block copolymer.

15

20